



## Product data sheet

Refractory applications –Mortars(Special Mortar)

Reference META07/06

# METAREF-95K

### Applications

- METAREF-95K is a chemical/ceramic bonded special mortar with alumina content of approximately 95%, which is used at high temperatures, in excess of 1800°C.
- It is used for setting porous plug, slide gate plate and for use in other critical areas.

### General characteristics

#### Chemical composition

##### Main constituents (%)

Al<sub>2</sub>O<sub>3</sub>- 95% min, Fe<sub>2</sub>O<sub>3</sub>- 0.1% max.

#### Physical properties

Grain Size	Bulk Density	Setting	Service Temperature	Water Addition	PCE Value	PLC Briquette size 25 X 25 X100 8% moisture dried at 110°C
0.1-0mm 95% must pass through 100 mesh B.S.S	2.8gm/cc	Chemical/ Ceramic Bonding	1800° C- 1950°C	20-25%	ORTON 40 min.	At 1550°C/2hrs± 0.5%

### Packaging

METAREF-95K does not contain any additives. METAREF-95K packaging is designed to protect it from moisture. However, it is recommended that METAREF-95K not be placed in direct contact with the ground. When correctly stored, the shelf life of METAREF-95K is at least 6 months. In most cases, its properties are retained for over a year.

Metaflux warrants that the products comply with the specifications stated herein to the exclusion of any other warranty, express or implied. Metaflux makes no representation or warranty of any kind, either express or implied, as to the merchantability or fitness for a particular purpose or use of the products. The warranty shall be limited to the replacement of the non-conforming products or, at Metaflux option, the refund of the purchase price. Any technical advice, recommendations or information are given based on Metaflux current knowledge and experience of the products and are deemed to be accurate. However, Metaflux undertakes no liability or responsibility of any kind in respect thereof. Users are invited to check that they have the latest version of this document.

**METAFLUX COMPANY PRIVATE LIMITED**

162, VIP Road, Kolkata-700054

Tel. No. + 91-33-2355-5799/0544/6252, Fax No. +91-33-2355-7636

e-mail id: [metaflux@vsnl.com](mailto:metaflux@vsnl.com), website: [www.metafluxco.com](http://www.metafluxco.com)